

Lag-Kote II

Asbestos Lagging Encapsulant

Product Description

6420-White

Lag-Kote II is a thick bridging encapsulant/sealant specifically formulated for application over interior friable Asbestos Containing Material (ACM). It is ideally suited to encapsulate interior pipe lagging, boiler jackets, breeching and other components of heating and ventilation systems. Its thick body minimizes dripping, cleanup and product waste while providing a smooth, washable, aesthetically superior finish that will provide years of protection. Lag-Kote II is a flexible coating that can be applied over galvanized metal, wood, masonry or other sound surfaces to prevent the release of harmful asbestos fibers.

Application Information

SURFACE PREPARATION

Warning! If you scrape, sand, or remove old paint from any surface, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH approved respirator to control lead exposure. Carefully clean up with a wet mop or HEPA vacuum. Before you start, find out how to protect yourself and you family by contacting the U.S. EPA/Lead Information Hotline at 1-800-424-LEAD (5323) or log on to www.epa.gov/lead.

SURFACE REPAIRS & CLEANING

Lagging that is torn, ruptured or delaminated should be repaired with:

1. Patching Cement: Mix cement with water and cap all exposed ends and voids.
2. Lag-Kloth Water-Activated Repair Cloth: Lag-Kloth should be dipped in water and applied to the asbestos containing material.

Upon completion of repairs, prepare the surface for the application of Lag-Kote II. Thoroughly remove all dust and dirt that has accumulated on lagging or covering, use a vacuum with a HEPA filter specifically designed to capture hazardous dust and waste or wipe surfaces with a damp cloth. Do not air clean surfaces; this could increase asbestos exposure.

APPLICATION TOOLS

Apply Lag-Kote II with brush, roller or airless spray equipment.

Brush: Synthetic, nylon or polyester bristle

Roller: Synthetic Fiber 3/8" nap or longer

Spray Settings:

Pressure: 2200-2700 P.S.I.

Tips: .017 to .021 tips

MIXING

Lag-Kote II may be diluted by adding up to 10% water. Prior to application, stir Lag-Kote II thoroughly to achieve a uniform consistency. Lag Kote II can be tinted to pastel colors.

PRODUCT APPLICATION

Select a brush, roller or painter's mitt for convenient application to the ACM. Apply 1-2 coats of Lag-Kote II to the desired film thickness. Minimum film thickness may vary with desired results and type of application.

COVERAGE

Smooth Surfaces: 125-175 sq. ft. per gallon

Porous Surfaces: 75-100 sq. ft. per gallon

DRYING TIME @ 70°F 50% R.H.

To Touch – 1-2 hours

Recoat – 8-16 hours

CLEANUP

Tools and drippings should be cleaned with warm soapy water before coating dries. Follow equipment manufacturer's directions to clean spray equipment. Dispose of all waste according to current Local, State and Federal regulations.

PRECAUTIONS

Store in a dry place at temperatures between 40°F (4.5°C) and 90°F (32°C). When applying with a sprayer, wear a NIOSH approved respirator with any R, P, N or HE filter. Approved respirators must be used to prevent inhalation of asbestos fibers that may be present in the air. Protective clothing should be worn. Careful consideration must be given to all EPA, OSHA, federal, state and local regulations in effect prior to the application of this product.

Properties

Product Specifications

Solids by Weight ± 2%:	52.0%
Solids by Volume ± 2%:	39.9%
Viscosity at 70°F:	120-130 Kreb Units
Specular Gloss:	45° ± 3 @ 60°
Flash Point:	Non-combustible
Shelf Life:	36 Months Min. (Original Sealed Container)
Calculated VOC:	89 grams/liter

Coverage

Smooth Surfaces:	125-175 ft ² /gal
Porous Surfaces:	75-100 ft ² /gal

Drying Times (@ 70 - 77°F , 50% R.H.)

To Touch:	1-2 hours
To Recoat:	8-16 hours
Minimum Application Temp:	50°F (10°C)

Available Package Sizes

2 Gallon Containers	
5 Gallon Containers	
Weight Per Gallon ± .5 lbs:	10.3 lbs/gal



Lag-Kote II

Asbestos Lagging Encapsulant

PRODUCT DATA SHEET

6420-White

Application Information

CAUTION!

KEEP OUT OF REACH OF CHILDREN.

Do not take internally. Close container after each use.

Keep from freezing.

Store between 40°F (4.5°C) and 90°F (32°C)

24 hour Emergency "CHEM-TEL" - 800.255.3924

For Technical Information call 800.342.3755

These suggestions and data are based on information we believe to be reliable. They are offered in good faith, but without guarantee, as conditions and methods of use of this product are beyond our control. Neither ICP Construction, Inc., nor its agents shall be responsible for the use or results of use of this product or any injury, loss or damage, direct or consequential. We recommend that the prospective user determine the suitability of this product for each specific project and for the health and safety of personnel working in the area.

Lag-Kote II, the Lag-Kote II Logo and other marks in this literature are trademarks of ICP Construction, Inc.

150 Dascomb Rd

•

Andover, MA 01810

•

www.fiberlock.com

•

800.342.3755