

CERAM™ 45 PLASTIC

Product Information Sheet

Monolithic Refractory

CERAM™ 45 is a super-duty chemically bonded plastic with quick dry-out capabilities.

Service Temperature: 2900 °F Material Required: 155 lb/ft³
 Typical Water Required: N/A % Maximum Grain Size: -

Chemical Analysis

SiO ₂	TiO ₂	Al ₂ O ₃	Fe ₂ O ₃	CaO	Na ₂ O + K ₂ O		
51.4 - 56.4	1.8 - 2.4	38.7 - 45.7	0.9 - 1.5	0 - 0.4	0.8 - 1.4		

--	--	--	--	--	--	--	--

Typical Physical Properties

Tested in accordance with International and ASTM Standards

Prefired to (°F)	Bulk Density (lb/ft ³)	Cold Crushing Strength (psi)	Cold Modulus of Rupture (psi)	Permanent Linear Change (%)
230	142	-	55	-0.3
1000	141	-	-	-0.3
1500	139	-	161	-0.3
2000	138	-	387	-0.4
2500	136	-	494	0.1

Other Physical Properties

Tested in accordance with International and ASTM Standards

Prefired to (°F)	Apparent Porosity (%)	Thermal Conductivity (Btu.in/h.ft ² .F)	Hot Modulus of Rupture (psi)	Permanent Volume Change (%)
230	-	7.2	-	-
1000	-	5.9	-	-
1500	-	6.2	-	-
2000	-	7.9	-	-
2500	-	11.1	-	-

Formerly: QUICKRAM® 45HS; CERAM™ 6; IFT™ PLASTIC

Product Number: LEV10098 MX1N MOLD
 Effective Date: 11/05/2003

MSDS Reference: LEV10098
 Revision: B:00

The physical and/or chemical properties and specifications of the product set forth above represent typical average results obtained in accordance with generally accepted standard test methods conducted under controlled conditions, and are subject to normal manufacturing variations. Vesuvius reserves the right to modify the properties and specifications at any time without prior notice.

NO WARRANTY IS EXPRESSED OR IMPLIED REGARDING THE ACCURACY OF THIS INFORMATION, THE SUITABILITY OF THE PRODUCT FOR A PARTICULAR PURPOSE, OR THE RESULTS TO BE OBTAINED BY THE USE OF THE PRODUCT. USERS EXPRESSLY ASSUME ALL RISKS AND LIABILITIES ARISING FROM THE USE OF OR RELIANCE UPON THIS INFORMATION.



VESUVIUS